

## Acculam® Accuply Product Data Sheet

Typical Properties	Typical Value	Units
<b>Physical Data</b>		
Tensile Strength MD	25,000 PSI	ASTM D 882 A
Tensile Strength TD	30,000 PSI	ASTM D 882 A
Elongation at Break MD	90 %	ASTM D 882 A
Elongation at Break TD	60 %	ASTM D 882 A
Yield Strength MD	14,000 PSI	ASTM D 882 A
Yield Strength TD	14,000 PSI	ASTM D 882 A
<b>Thermal</b>		
Shrinkage MD ( 190 °C )	2.8 %	Unrestrained 5 minutes
Shrinkage MD ( 190 °C )	0 %	Unrestrained 5 minutes
Melt Point	260 °C	

**Notes:** The typical values stated above apply to Accuply® 10. Accurate Plastics does not assume liability, obligation or imply guarantee with regard to the above information.

**Product Description:** Acculam® Accuply is a multi-use, matte finish, double-sided film that will release from most synthetic resin systems: epoxies, phenolic, melamines, rubber, etc. For use in hand layup, from 0 pressure to high-pressure applications (1500 PSI) and temperatures to 204 °C (400 °F).

**Typical Applications:** Lamination of thermoset plastics, rubber and most synthetic resins. Highly versatile

• **QUALITY** • **VALUE** • **SPEED** • **ACCURATE**

*Accurate provides this data as information only and does not imply any warranty for its use or application.*