

Acculam® Phenolfab X / XX

Product Data Sheet

Typical Properties	Typical Value	Units
Physical Data		
Specific Gravity	1.36	---
Water Absorption -.125"	<1.3	%
Temperature Index	140 / 284	°C / °F
Rockwell Hardness	110	M scale
Bond Strength	>800 / 363	lbs / kgs
Flexural Strength -LW -A -.125"	>19,000 / 131	PSI / MPa
Flexural Strength -CW -A -.125"	>18,000 / 124	PSI / MPa
Izod Impact Strength -LW	>.55	ft-lbs / in
Izod Impact Strength -CW	>.50	ft-lbs / in
Compressive Strength -Flatwise	>34,000 / 234	PSI / MPa
Electrical Data		
Dielectric Breakdown -A	>40	kV
Dielectric Breakdown -D48/50	>5.0	kV
Permittivity A	<5.50	
Permittivity -D24/23	<6.00	
Dissipation Factor -A	<.045	
Dissipation Factor -D24/23	<.050	

Product Description: Acculam® Phenolfab X/XX - Laminate sheet comprised of a phenolic resin binder and a saturating kraft (paper) substrate. It qualifies to NEMA X/XX and MIL-I-24768/11/12.

Typical Applications: This is a general purpose grade with good mechanical and electrical insulating properties. Its versatility, good machining characteristics and lower cost encourage its applications as switch plates, barriers, terminal strips, washers and other electrical components.

• **QUALITY** • **VALUE** • **SPEED** • **ACCURATE**

Accurate provides this data as information only and does not imply any warranty for its use or application.