

Acculam® Siliglas G7 Product Data Sheet

Typical Properties	Typical Value	Units
Physical Data		
Specific Gravity	1.75	---
Water Absorption -.125"	<0.35	%
Temperature Index	220 / 428	°C / °F
Rockwell Hardness	100	M scale
Bond Strength	>700 / 320	lbs / kgs
Flexural Strength -LW -A -.125"	>24,000 / 166	PSI / MPa
Flexural Strength -CW -A -.125"	>18,000 / 124	PSI / MPa
Izod Impact Strength -LW	>10	ft-lbs / in
Izod Impact Strength -CW	>8	ft-lbs / in
Compressive Strength -Flatwise	>45,000 / 310	PSI / MPa
Electrical Data		
Dielectric Breakdown -A	>50	kV
Dielectric Breakdown -D48/50	>40	kV
Permittivity A	<4.0	
Arc Resistance -A	>180	SEC
Dissipation Factor -A	0.003	
Dissipation Factor -D24/23	0.020	

Product Description: Acculam® Siliglas G7 - Laminate sheet comprised of a high performance silicone resin and a woven fiberglass substrate. It qualifies to NEMA G-7 and MIL-I-24768/17.

Typical Applications: This material has high heat resistance, low dissipation factor, and excellent arc resistance. It is flame resistant with low smoke evolution, and meets the needs of Class "H" insulation. It is used in high frequency telecom equipment, transformers and items subjected to high heat

• **QUALITY** • **VALUE** • **SPEED** • **ACCURATE**

Accurate provides this data as information only and does not imply any warranty for its use or application.